

# *Andrew S. McCreath & Son, Inc.*

ANALYTICAL AND CONSULTING CHEMISTS

610 Willow Street  
P.O. Box 1453  
Harrisburg, PA 17105-1453  
Telephone: (717) 238-9331  
Telex: 84-2321  
Fax: (717) 238-4843

## Analysis Report

July 21, 2005

J2 Engineering, Inc.  
285 NW 138th Terrace - Suite 100  
Jonesville, Florida 32669

Gentlemen:


The sample of Low Carbon Ferro Chrome taken by our representative on July 6, 7, 8, 11, 12, 13, 14, 2005, from Stockpile #4AB - approximately 5,930.19 Short Tons, at Somerville, New Jersey as it arrived from Belle Mead, New Jersey, contained dried at 105°C:

Chromium	70.96%
Carbon	0.089%
Silicon	0.54%
Phosphorus	0.025%
Sulphur	0.009%

Lab #05071902

Yours very truly,

**ANDREW S. McCREATH & SON, INC.**



# *Andrew S. McCreath & Son, Inc.*

ANALYTICAL AND CONSULTING CHEMISTS

610 Willow Street  
P.O. Box 1453  
Harrisburg, PA 17105-1453  
Telephone: (717) 238-9331  
Telex: 84-2321  
Fax: (717) 238-4843

## Analysis Report

January 17, 2005

RECEIVED JAN 24 2005

J2 Engineering, Inc.  
285 NW 138th Terrace - Suite 100  
Jonesville, Florida 32669

Gentlemen:


The sample of Low Carbon Ferro Chrome taken by our representative on January 4, 5, 6, 7, 2005, from Stockpile 57 - approximately 4,412.04 Short Tons, at Point Pleasant, West Virginia, contained dried at 105°C:

Chromium	69.38%
Carbon	0.10%
Silicon	0.65%
Phosphorus	0.025%
Sulphur	0.002%

Lab #05011101

Yours very truly,

ANDREW S. McCREATH & SON, INC.



# Andrew S. McCreath & Son, Inc.

ANALYTICAL AND CONSULTING CHEMISTS

610 Willow Street  
P.O. Box 1453  
Harrisburg, PA 17105-1453  
Telephone: (717) 238-9333  
Telex: 84-2321  
Fax: (717) 238-4843

## Analysis Report

April 14, 2005

J2 Engineering, Inc.  
285 NW 138th Terrace - Suite 100  
Jonesville, Florida 32669

Gentlemen:


The sample of Low Carbon Ferro Chrome taken by our representative on March 31, April 1, 4, 5, 2005, from Stockpile 022-D - approximately 5,000.00 Short Tons, at Ravenna, Ohio, contained dried at 105°C:

Chromium	65.45%
Carbon	0.14%
Silicon	0.73%
Phosphorus	0.022%
Sulphur	0.001%

Lab #05040801

Yours very truly,

ANDREW S. McCREATH & SON, INC.



*Andrew S. McCreath & Son, Inc.*

ANALYTICAL AND CONSULTING CHEMISTS

610 Willow Street  
P.O. Box 1453  
Harrisburg, PA 17105-1453  
Telephone: (717) 238-9331  
Telex: 84-2321  
Fax: (717) 238-4843

Analysis Report

May 31, 2005

J2 Engineering, Inc.  
285 NW 138th Terrace - Suite 100  
Jonesville, Florida 32669

Gentlemen:

The sample of Low Carbon Ferro Chrome taken by our representative on May 18, 19, 20, 2005, from Stockpile #112A - approximately 5,000 Short Tons, at New Haven, Indiana, contained dried at 105°C:

Chromium	68.62%
Carbon	0.091%
Silicon	0.60%
Phosphorus	0.019%
Sulphur	0.001%

Lab #05052406

Yours very truly,

ANDREW S. McCREATH & SON, INC.